



CARACTERÍSTICAS TÍPICAS INTER - LEAVING

Fecha de revisión 24.10.05

UNE/EN/ISO-536	Gramaje	g/m ²	50	+/-4%
UNE/EN-20287	Humedad	%	6.5	+/-1,5
UNE/EN/ISO-1924-2	Alargamiento SM	%	1.7	-10%
UNE/EN/ISO-1924-2	Alargamiento ST	%	6.9	-10%
UNE/EN/ISO-1924-2	Long.Rotura SM	m	6.000	-10%
UNE/EN/ISO-1924-2	Long.Rotura ST	m	3.000	-10%
UNE/EN21974	Ind.Rasgado SM	mNm ² /g	13	-10%
UNE/EN-21974	Ind.Rasgado ST	mNm ² /g	13	-10%
UNE/EN-20535	CoBB 60 C	g/m ²	25	Max.40
UNE/EN-20535	CoBB 60 T	g/m ²	25	Max.40

UNE/EN-20187	ACONDICIONAMIENTO DE MUESTRAS			
	Humedad relativa	%	50.0	+/-2%
	Temperatura	°C	23.0	+/-1°C



